



Unifast–TC Quick-Drying

Product Descriptions: -A quick drying finish coat. Dries very fast based on fast drying Synthetic resin. This is a one pack coating system.

Intended Uses: - Can be used for wide variety of application where economy as well as fast production rate is required. Suitable for new steel structures as well as maintenance finish also.

Product Information: -Colours	Wide range of colours
Finish/Sheen	High Gloss / Semi Gloss / Matt
Volume Solids	35% \pm 0 % (May Vary as per shade)
Mix Ratio	Not applicable
Typical Film Thickness	25-30 microns dry
Theoretical Coverage	10 (m ² /lt) at 30 microns dft, allow appropriate loss factors
Method of Application	Spray, Brush, Roller

Dying Information: - 30°C

Touch dry : -	10 minute
Tack Free : -	2-3 Hours
Hard Dry : -	Over night
Pot Life : -	Not applicable



Unifast–TC

Quick-Drying

Direction for use

1. Ensure the surface to be painted is free from any loose paint, dust or grease
 2. Stir well the paint thoroughly in the container.
 3. Adjust the viscosity 20-22 Sec. Mix the thinner with paint as per recommended ratio (i.e.; 25% by volume) for spraying.
 4. Stain the paint with bloating nylon no. 40.
 5. Apply two coats of the paint on the surface.
 6. Keep the pressure to 2.8 - 3.5 kg / sq. cm. & air should be completely dry and free from moisture.
-

Warning: -

Flammable liquid and vapor
Cause: - Eye irritation
May cause skin irritation

First aid: -

- 1. For Eyes:** - 1. Immediately flush with plenty water
2. Get medical attention
3. Remove affected cloths
- 2. On Skin:** - 1. Immediately flush with plenty of water
2. Remove contaminated clothing.
3. Wash clothing before using.
-

Handling: -

Keep away from heat, sparks and flame.
Avoid contact with eyes, skin and clothing.

Storage: -

Keep in a cool, dry and ventilated place.
Stable under normal condition.

Precautions: -

Do not add any thinner or material in paint, which is not recommended